


P.E FOAM
DUNALON
BACK-UP MATERIALS(ROD)
INSULATION PIPE COVER



DUNALON is chemically non-crosslinked polyethylene foam with closed cells, expanded 15 or 40 times. It is a light and durable material with excellent shockabsorbing and heat insulation properties. Water-repellent and highly resistant to weather-proof and chemicals.

DUNALON is protective against the Penetration of gasoline and inorganic solutions.

STANDARD SIZE

| Form | Diameter(MM) | Length |
|------------|-----------------|-------------|
| Back-up | 5-100 | not limited |
| Pipe cover | 8-80(Inside) | not limited |
| | 20-100(Outside) | not limited |


Standards not indicated above are still possible to make, at our customer's request.

APPLICATIONS


Used as sealant and gasket material in various applications.

- * Window and sash frames glass reinforcement.
- * Expansion joints in rooftops, tunnels, subways, bridges, etc.
- * Joints in water ways, cleaning beds, storing reservoirs, swimming pools, dams, sewage systems etc.
- * Window frames and joints in automobiles, trains, containers, etc.

PRE-CASTED BOARD AND CREVICES



SASH FRAME OF GLASS WINDOW



Sealant is compressed and holds the stacking form, and so the tension strength works on parts and the adherence part can not be removed even in case of vibration.

PROPERTIES

| Properties | Unit | Result | Properties | Unit | Result |
|---------------------------|--------------------|-----------|----------------------|--------------------|-------------|
| Expansion ratio | times | 15-40 | Resiliency | | 30-48 |
| Specific gravity | g/cm ³ | 0.03-0.05 | Thermal conductivity | 0°C, kcal/mh°C | 0.025-0.034 |
| Tensile strength | kg/cm ² | 2.8-4.1 | Shrinkage at 70°C | % | 0.3 |
| Elongation | % | 240-250 | Water absorption | mg/cm ² | 0.01 |
| Compression strength | kg/cm ² | 2.9-3.5 | Volume resistance | cm | 1017 |
| Compression set | % | 3.0-6.6 | Dielectric constant | 106c/s | 1.1 |
| Repeating compression set | % | 3.9-8.6 | Power factor | 106c/s% | 0.01 |

DUNALON ROD DIAMETER & PACKING (Meter/Roll)

| Type | Size(mm) | | Meter/Roll |
|------|----------|------------|------------|
| | Rod Dia. | Joint Size | |
| D306 | 6 | 4-5 | 2,100 |
| D308 | 8 | 5-7 | 1,000 |
| D310 | 10 | 7-8 | 1,000 |
| D313 | 13 | 9-10 | 500 |
| D135 | 15 | 11-13 | 500 |
| D320 | 20 | 14-16 | 4×200pcs |
| D325 | 25 | 18-20 | 4×100pcs |
| D330 | 30 | 21-25 | 4×100pcs |
| D340 | 40 | 30-35 | 4×150pcs |
| D350 | 50 | 40-45 | 4×25pcs |






COLOR

- * The standard color is white(natural color)
- * Any color such as black, blue, yellow, green and ivory available, according to at our customers request.

**HOW TO
MAKE USE OF
"PE FOAM
DUNALON"
BACK-UP MATERIALS
& PIPE COVER**

HEAT CONDUCTION RATIO OF DUNALON



ADVANTAGES

- Universality applicable
- Considerable work saving
- Simple and rapid application
- No clumsy work with adhesive or glue
- Excellent chemical resistance and weatherability
- Absorbs no moisture
- Prevents condensation and oxidation
- Suitable for cold as well as heat conducting pipe lines(-72°C to +88°C)

APPLICATIONS

- Central heating pipes
- Sanitary pipes
- Water supply
- Solar system
- Pipes and air ducts of refrigeration and conditioning installations



株式会社斗南

DUNALON DUNAM PLASTIC CO., LTD.

- HEAD OFFICE: 38-6, NAMDONG INDUSTRIAL ESTATE, NAMDONG-KU, SEOUL, KOREA
TEL: (02)432-7826, FAX: (02)432-7830
- SEDUL OFFICE: 156-1, 4ga, YANGBYUNG-DONG, YECUNGDENGPO-SI, SEOUL, KOREA
TEL: (02)675-3488/9, 675-3867, 675-5565, FAX: (02)675-5611, (02)552-5336
- BRANCH : PUSAN: TEL: (051)50-1350, FAX: (051)5-4-6237

E-mail: dunalon@kotis.net
Homepage: www.dunam.com